



MYK LATICRETE

LATAFIX 305 Thin-set Adhesive



Polymer based thin-set adhesive for fixing ceramic tiles and small format stone on interior floor & wall.

Features / Benefits

- Single component, just add water
- Interior applications, polymer based
- Economical & Easy to use
- Bonds to various substrates
- Exceeds ANSI A118.1T shear bond strength requirements
- Complies with EN / ISO with a C1T classification.
- Exceeds IS 15477 – Type 1 Adhesive standards.
- Can be fortified with latex admix for external Tile and Stone installations.

Application

Designed especially for interior floor and wall installations of all types of ceramic tile, semi-vitreous tile, precast terrazzo and small format natural stones over concrete and on a variety of cement based substrates.

Substrates

- Concrete
- Concrete Masonry
- Cement Mortar Beds
- Cement Plaster
- Existing Vitrified Tile* & Ceramic Tile*
- Brick Masonry
- Cement Terrazzo
- Existing Natural Stone*

* Surface to be cleaned and roughened before installation of tiles or stones.

Certifications

IS 15477
Type: 1

EN / ISO: C1T

Member of
Indian Green Building Council



A118.1T

PERFORMANCE PROPERTIES

LATAFIX 305 Adhesive mixed with Water

Applicable Standards:

ANSI A118.1-1999; EN 12004 & ISO 13007; IS15477

ANSI Data		
Property : Test method	Requirement	Typical Values
Open Time (20 Minutes at 28 days): ANSI A118.1 Clause – 5.3	≥75 psi (0.50 Mpa)	95 psi – 100 psi (0.65 – 0.69 Mpa)
Sag: ANSI A118.1- Clause 6.0	≤0.02 Inches (0.50 mm)	0.016 – 0.018 Inches (0.40-0.45 mm)
Glazed wall tile Shear Strength		
7 Days: ANSI A118.1 – Clause 7.1.2	>200psi (1.38Mpa)	200-225 psi (1.38 Mpa-1.55 Mpa)
7 Days Water immersion: ANSI A118.1- Clause 7.1.3)	>150psi (1.03Mpa)	150-175 psi (1.03 Mpa-1.20 Mpa)
Porcelain Mosaic Tile Shear Strength		
1 Day: ANSI A118.1 – Clause 7.2.2	>50psi (0.34Mpa)	50 -75 psi (0.34 Mpa-0.51 Mpa)
7 Days: ANSI A118.1 – Clause 7.2.3	>150psi (1.03Mpa)	150-175 psi (1.03 Mpa-1.20 Mpa)
7 Days Water immersion: ANSI A118.1 – Clause 7.2.4	>100psi (0.69Mpa)	125-150 psi (0.86 Mpa-1.03 Mpa)
28 Days: ANSI A118.1 – Clause 7.2.5	>150psi (1.03Mpa)	150-175 psi (1.03 Mpa-1.20 Mpa)
12 Weeks: ANSI A118.1 – Clause 7.2.6	>150psi (1.03Mpa)	150-175 psi (1.03 Mpa-1.20 Mpa)

The adhesive mortar conforms to ANSI A 118.1T

EN / ISO Data		
Property: Test Method	Requirement	Typical Values
Open Time: EN 1346	≥0.50 N/mm ²	0.65 – 0.69 N/mm ²
Slip Resistance: EN 1308	≤0.50 mm	0.40-0.45 mm
Tensile Adhesion Strength		
Initial: EN 1348 – Clause 8.2	≥0.50 N/mm ²	0.50 – 0.60 N/mm ²
After Water Immersion : EN 1348 - Clause 8.3	≥0.50 N/mm ²	0.50 – 0.60 N/mm ²
Heat Ageing: EN 1348 – Clause 8.4	≥0.50 N/mm ²	0.50 – 0.60 N/mm ²
Freeze- Thaw: EN 1348 – Clause 8.5	≥0.50 N/mm ²	0.50 – 0.60 N/mm ²

The adhesive mortar conforms to EN12004 / ISO 13007 as C1T

IS Data		
Property : Test method	Requirement	Typical Values
Tensile Adhesion		
Dry Conditions (14 Days Std.) – Annex A (Clause 4.4)	Min.750 N	775 – 800 N
Wet Conditions (7 Days Std + 7 Days Water) – Annex A (Clause 4.4)	Min.450 N	475 – 500 N
Shear Adhesion		
Dry Conditions (24 Hours) – Annex B (Clause 4.5)	Min.2.5 kN	2.75 – 3.00 kN
Dry Conditions (14 Days) – Annex B (Clause 4.5)	Min.8.00 kN	8.25 – 8.50 kN
Heat Ageing (7 Days Std + 7 Days Oven) – Annex B (Clause 4.5)	Min.4.00 kN	4.25 – 4.50 kN
Wet Conditions (7 Days Std + 7 Days Water) – Annex B (Clause 4.5)	Min.4.00 kN	4.25 – 4.50kN

The Adhesive mortar conforms to IS 15477: Type 1 Adhesive

Packaging:

20 kg & 50 kg bags

Colour:

Grey and white

Coverage:

Approx 55-60 sft per 20kg bag with 1/4" x 1/4" (6mm x 6mm) square notched trowel for average bed of 3mm.

Coverage will vary depending on trowel notch size, type and size of tile and substrate smoothness and evenness.

Working Properties at 70° F (21° C)

LATAFIX 305 Adhesive mixed with Water

Open Time	20 minutes
Pot Life	2 - 3 Hours
Time to Heavy Traffic	16 - 24 hours

Specifications subject to change without notification.

Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

INSTALLATION

Surface Preparation:

All surfaces should be between 40° F(4°C) and 104° F(40°C) and structurally sound, clean and free of all dirt, oil, grease, loose peeling paint, laitance, concrete sealers or curing compounds.

Check the surface to be true to plumb. All slabs must be plumb and true to within ¼”(6mm) in 10 ft(3m). Rough or uneven concrete surfaces should be made smooth with MYK LATICRETE® Screed/Plaster material to provide a wood float (or better) finish.

Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28* days old before application.

*No minimum cure time for concrete slabs when thin-set mortar is mixed with latex additive.

Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Do not cover expansion joints with thin set mortar. Follow ANSI Specification AN-3.8 “Requirements for Expansion Joints” or TCA Detail EJ171 “Expansion Joints”. For tile installation over Cement Backer Board: follow TCA installation details W244.

NOTE: For tile or stone installations on plywood and wood substrates, MYK LATICRETE DWA 215 OR MYK LATICRETE PUA 212 is recommended. Please refer specific product Technical Data Sheet for detailed recommendations.

Mixing:

Place clean, potable water into a clean mixing bowl. Add LATAFIX 305 powder into the mixing bowl. Use approximately 5.5 - 6L of water for 20 kg of powder.

Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow adhesive to slake for 5-10 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

Note: Addition of LATICRETE® latex admix*, partially or completely replacing water would enhance the bond strength, flexibility of the thinset mortar.

* Contact MYK LATICRETE technical services for large format tile or stone installations on exterior surfaces.

APPLICATION

Apply adhesive to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional adhesive with the notched side. Use the proper sized notched trowel to ensure full bedding of the tile. Spread as much adhesive as can be covered with tile in 10 minutes. Back butter large format tiles (> 12”x12”) to provide full bedding and firm support. Place tiles into wet, sticky adhesive and beat in using a beating block and rubber mallet to imbed tile and adjust level. Check adhesive for complete coverage by periodically removing a tile and inspecting bedding adhesive transfer onto back of tile. Use of MYK LATICRETE spacer is recommended to provide grout joints between tiles / stones. The joint width shall be as per the recommendation of architect / engineer. Remove the spacers when the adhesive is set firm.

If adhesive is skinned over (not sticky), remove and replace with fresh adhesive.

For highly absorbent natural stones which may form a wet patch when adhesive is used, it is recommended to use suitable Laticrete Impregnating sealers on all sides. LATICRETE 3642 Latex admix can also be used as a bottom coat for natural stones to prevent or reduce wet patches during installation. Please refer Technical Data Sheets of product intended for use for specific instructions of use

HOT & COLD WEATHER TILING:

* Please refer technical document on Hot & Cold weather tiling

Grouting:

Grout installation shall be commenced after a minimum of 24 hours curing time at 70°F (21° C). Grout with MYK LATICRETE® Sanded or Unsanded Grout mixed with MYK LATICRETE® 1776 Grout Admix Plus.

For maximum stain resistance of Internal spacer joints applications, use SpectraLOCK® Pro Premium Grout OR MYK LATICRETE Stellar grout OR LATAPOXY® SP-100 Stainfree Grout.

CUSTOMER CARE

MYK LATICRETE India Pvt Ltd.

8-2-703/A, Fourth Floor, Leela Gopal Towers,
Road No-12, Banjara Hills, Hyderabad – 500034
(T.S) Tel: +91-40-30413100

Customer Care: cc@myklaticrete.com

Website: www.myklaticrete.com